

IN THE CLAIMS

Replace the claims with the following rewritten listing:

1. (Original) A fibre insulation material for the manufacture of a non-woven fibreboard comprising primary fibre components of
 - a portion of 50 % to 90 % cellulose fibres;
 - 2 % to 20 % synthetic fibres, said synthetic fibres preferably being crimped fibres and having a length between 12 to 75 mm; and
 - 2 % to 20 % bi-component fibres comprising a core and an outer sheathing, said outer sheathing having a lower melting point than the core.
2. (Previously Presented) A fibre insulation material according to claim 1, wherein said synthetic fibres are provided with fire-retarding chemical.
3. (Previously Presented) A fibre insulation material according to claim 2, wherein said cellulose fibres are saturated with the fire-retarding chemical.
4. (Previously Presented) A fibre insulation material according to claim 2, wherein the content of the fire-retarding chemical is between 1 and 30 of the total fibre material composition.
5. (Previously Presented) A fibre insulation material according to claim 1, wherein said cellulose fibres having a length between 1 to 10 mm.
6. (Previously Presented) A fibre insulation material according to claim 1, wherein said bicomponent fibres having a length between 1 to 10 mm.
7. (Previously Presented) A fibre insulation material according to claim 1, wherein said fibre board material is manufactured with a grammar weight of 10 to 50 kg/m³.

8. (Previously Presented) A fibre insulation material according to claim 1, wherein said synthetic fibres are hollow.
9. (Previously Presented) A fibre insulation material according to claim 1, wherein said crimped synthetic fibres are essentially helically shaped.
10. (Withdrawn) A method of manufacturing a fibre board made of a material according to claim 1, whereby the material is laid onto a forming wire in an air-laid dry forming process and cured in a heat treatment process in which the formed fibre board is subjected to an air circulation with air heated to a temperature of 90°C to 145°C.
11. (Previously Presented) A fibre insulation material according to claim 6 wherein said bicomponent fibres have a length of approximately 3mm.
12. (Withdrawn) The method of claim 10, wherein the fibre board is subjected to the air circulation with the air heated to a temperature of approximately 130°C.
13. (Previously Presented) A fibre insulation material according to claim 2, wherein said fire-retarding chemical comprises at least one of Borax, Boric acid, Ammonium sulphate and aluminium sulphate mixed with said synthetic fibres.